

OK TO ENTER: /J.M./

IN THE CLAIMS

1. (Previously presented) An aluminium alloy product with high strength and fracture toughness and a good corrosion resistance, said alloy consisting of, in weight %:

Zn	7.2 to 7.43
Mg	1.92 to 2.1
Cu	1.43 to 1.80
Zr	about 0.06 to 0.1
Fe	< about 0.08
Si	< about 0.07
Mn	0.05 to 0.11

and other impurities or incidental elements each < 0.05, total < 0.15, and the balance being aluminium.

2-6. (Cancelled)

7. (Previously presented) Aluminium alloy product according to claim 1, wherein
Mg 1.92 to 1.95.

8. (Currently amended) Aluminium alloy product according to claim [[5]] 1, wherein
Mg 1.92 to 1.95
Cu 1.43 to 1.75.

9-27. (Cancelled)

28. (Previously presented) An aluminium alloy product according to claim 1, said alloy consisting of, in weight %:

Zn	7.2 to 7.43
Mg	1.92 to 2.1
Cu	1.43 to 1.75
Zr	about 0.06 to 0.10